

Elite Aqua-Matt -Technical Data & Specification Sheet

Contact Pristine Coatings on 01492 544777

Product Name: Elite Aqua-Matt stain covering, waterbased, high opacity coating for interiors.

Supplier: Pristine Coatings, Unit 10 Phoenix Workshops, Station Rd, Mochdre, Colwyn Bay, LL28 5EF. Tel 01492 544777

Description: Elite Aqua-Matt is a problem solving stain covering waterbased coating. It is self priming and has been designed to cover light nicotine, smoke, fire damage & graffiti without the need to washing down, or priming. Aqua Matt is without doubt the best stain blocking problem solving waterbased product on the market today. Aqua-matt offers a 100% matt flat finish. Can also be sprayed onto new damp plaster.

Where to Use: Plasterboard, concrete, plaster, cladding, suspended ceilings, wood, existing paint films, wallpaper & galvanised.

Properties:

- Excellent stain covering, inc nicotine, smoke & fire damage
- Waterbased
- Flat matt uniform finish with no roller marks
- Excellent productivity
- Self priming finish coat
- Durability
- washable
- Will not flake or peel
- Vapour permeable

Specification

Preparation: brush down the surface to remove all dust, cobwebs etc, de-grease any heavy contamination, spot prime any bare steel or seal any wet watermarks, mask up if product to be applied by spray.

Application:

Aqua-Matt can be applied by brush, roller or airless spray. For brush and roller application do not dilute, apply a 50 / 50 mist coat then one full coat to finish. Aqua-Matt should remove the need for a 2nd topcoat

If applied by airless spray use a 0.13 to 0.15 tip, dilute by 5% and apply one full coat overlapping each pass by 50%. This should be sufficient. However depending on the substrate a further mist coat may be required to complete the project.

Completion: Clean brush, roller & machine with warm water, clean area ready for re-occupation.

Tech data:

Colour	White as standard but can be supplied in any RAL or BS colour
Solids	52%
Spread rate	6m ² per litre depending on WFT Required.
Dry to touch	30 minutes
Recoat after	2 hours
Clean-up	Warm Soapy Water
Flash Point	100°C
WFT	between 250 microns
Containers	15 litres
Weight	23 Kilos

